

# CHIMEI

奇美實業股份有限公司

CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN.  
TEL: 886-6-266-5000 FAX: 886-6-266-5555-7

## Typical Properties of WONDERLITE® PC

Properties	ISO	Din	Unit	Test Method	WONDERLITE® PC									
					Extrusion		General Purpose			UV Resistant			SAE Approved	Flame Retardant
					PC-108	PC-108U	PC-110	PC-115	PC-122	PC-110U	PC-115U	PC-122U	PC-110L	PC-110V
Melt Volume-Flow Rate	1133		cm <sup>3</sup> /10 min	300°C×1.2 Kg	6.5	6.5	10	15	22	10	15	22	10	10
Vicat Softening Temp.	306	53460	°C	1 Kg, 50°C/hr	150	148	150	150	150	148	148	148	148	150
			°C	5 Kg, 50°C/hr	145	143	145	145	145	143	143	143	143	143
H.D.T	75	53461	°C	1.80MPa, unanneal	128	127	128	128	128	127	127	127	127	128
			°C	1.80MPa, anneal	143	142	143	143	143	142	142	142	142	142
Izod Impact Strength	180/1A	—	KJ/m <sup>2</sup>	1/8" notched	80	80	80	75	70	80	75	70	80	80
	180/1U	—		1/8" unnotched	—	—	—	—	—	—	—	—	—	—
Charpy Impact Strength	179	—	KJ/m <sup>2</sup>	Notched	75	75	75	70	60	75	70	60	75	75
		—		Unnotched	—	—	—	—	—	—	—	—	—	—
Tensile Strength	527	53455	MPa	50mm/min,yield	65	65	65	64	63	65	64	63	65	65
			MPa	50mm/min,break	75	75	75	70	70	75	70	70	75	75
Tensile Elongation	527	53455	%	50mm/min	120	120	120	120	120	120	120	120	120	120
Flexural Strength	178	53452	MPa	2mm/min	90	90	90	90	90	90	90	90	90	90
Flexural Modulus	178	53452	MPa	2mm/min	2400	2400	2400	2400	2400	2400	2400	2400	2400	2400
Ball Indentation Hardness	2039-1	53456	N/mm <sup>2</sup>	H358/30	100	100	100	101	102	100	101	102	100	100
Flammability			—	UL-94	1.5mm HB 3.0mm HB	1.5mm HB 3.0mm HB	1.5mm V-2 2.5mm V-2	0.4mm V-2 1.5mm V-2 2.5mm V-2	1.6mm V-2 3.2mm V-2	0.75mm V-2 1.5mm V-2	0.75mm V-2 1.5mm V-2	0.75mm V-2 3.0mm V-2	1.5mm V-2	1.5mm V-2 3.0mm V-2 6.0mm V-0
Mass Density	1183	53479-A	g/cm <sup>3</sup>		1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2	1.2
Characteristics/Principal Applications					High Viscosity	UV Stabilized	Medium Viscosity	Low Viscosity	High Flow	UV Stabilized	UV Stabilized	UV Stabilized	SAE Approved	3.0mm V-2

Note : This Technical data sheet shown above is for reference only.

## Chi Mei Wonderlite® PC-110 Polycarbonate


**Categories:** [Polymer](#); [Thermoplastic](#); [Polycarbonate](#)

**Material Notes:** Medium Viscosity

**Vendors:** No vendors are listed for this material. Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ISO 1183
Melt Flow	10.0 g/10 min @Load 1.20 kg, Temperature 300 °C	10.0 g/10 min @Load 2.65 lb, Temperature 572 °F	Melt Volume Rate (ml/10 min); ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	100 MPa	14500 psi	H358/30; ISO 2039-1
Tensile Strength at Break	75.0 MPa	10900 psi	50 mm/min; ISO 527
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Flexural Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Charpy Impact, Notched	7.50 J/cm <sup>2</sup>	35.7 ft-lb/in <sup>2</sup>	ISO 179
Izod Impact, Notched (ISO)	80.0 kJ/m <sup>2</sup>	38.1 ft-lb/in <sup>2</sup>	ISO 180/4A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	128 °C	262 °F	annealed; ISO 75
	143 °C	289 °F	unannealed; ISO 75
Vicat Softening Point 	145 °C @Load 5.00 kg	293 °F @Load 11.0 lb	50 °C/hr; ISO 306
	150 °C @Load 1.00 kg	302 °F @Load 2.20 lb	50 °C/hr; ISO 306
Flammability, UL94	V-2 @Thickness 2.54 mm	V-2 @Thickness 0.100 in	

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's [terms of use](#) regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.