

ABS SD0150 is one of the styrenic terpolymer (ABS) grade with improved toughness versus HIPS grades. ABS SD0150 exhibits, low shrinkage, and good dimensional stability. ABS SD0150 is widely used in general injection molding applications. Use this information as a guide to aid you in selecting the proper resin for your application.

Drying:

Drying prior to processing is recommended in a desiccant dehumidifying hopper dryer. An inlet air dew point of -20°F (-29°C) or below is recommended to achieve a moisture content 0.1%. Typical drying conditions are 2 hours at 180° - 190°F (82° - 88°C). Drying for 4 hours at 160° - 170°F (71°-77°C) is also adequate.

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX (200°C/5KG)	GR/10MIN	ASTM D-1238	1.8
IZOD IMPACT STRENGTH	KJ/M2	ASTM D-256	22
VICAT SOFTENING POINT(50N LOAD)	°C	ASTM D-1525	98
BULK DENSITY	KG/M3	-	600
TENSILE STRENGTH AT YEILD	KGF/CM2	ASTM D-638	450
ROCKWELL HARDNESS(AT 23°C)	R.SCALE	ASTM D-785	105


Applications:

Furniture, Automotive Parts , General Injection Molding, Appliances Casing, Office Supplies.



 Unit 302, Sheydayee BLD, Sazman AB, Tehranpars

 <https://irplastics.com/en>

 +98-21-77784838

