



Doc Cod: ED-FO-04/00

# CERTIFICATE OF ANALYSIS

To:  
Sco ia General Trading

## Laboratory Analysis

### Specification

Customer ID:

....

Product:

Jampilen EP548R

Melt Flow Index (230°C, 2.16Kg)	ASTM D1238	19.5	g/10min	Min 18 -Max 24
Tensile Strength at Yield	ASTM D638	26.41	MPa	Min 22
Tensile Elongation at Yield	ASTM D638	6.88	%	Min 4
Flexural Modulus	ASTM D790	1325	MPa	Min 1200
Izod Impact (23°C)	ASTM D256	143.23	J/m	Min 80
H.D.T	ASTM D648	115.7	°C	Min 95
Vicat	ASTMD1525	152.6	°C	Min 140

Lot number:  
99098

This material has been classified as standard product quality meeting Jam Polypropylene Company requirements for this product. Please contact our Product Engineering division to ask further technical information.

Production date:  
18.05.2020

Engineering and Business Development Dept.  
Jam Polypropylene Company  
Phone: (+98-21) 84287230  
Fax: (+98-21) 88563100  
Email: [technicalsupport@jppc.ir](mailto:technicalsupport@jppc.ir)  
Website: <http://www.jppc.ir>



This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness or a particular purpose. This data does not absolve the purchaser from checking the quality of all supplies immediately on receipt, particularly regarding the possible influences of storage conditions over which we have no control.