



## HDPE made via Hostalen Process



### Product data sheet HF7750M

- production monofilaments with high tensile Strength.

HDPE: HF7750M

Density: 0.956

MFI: 2.5±0.3

#### Features



----

#### Applications



- Monofilament

#### Additives



- Antioxidant / Process stabilizer
- Lubricant (processing aid) / acid scavenger

**Material properties** (This data are typical values and are not to be construed as product specifications.)

120

Test/Composition	Typical Value	Unit	Method
Density	0.956	g/cm <sup>3</sup>	ISO 1183
Fish Eye Note	≤ 5	Note	internal
FRR 21.6/5	10		
MFR 190° /21.6	25	g/10min	ISO1133
MFR190° /5	2.5	g/10min	ISO1133

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .