

# KP Plastics

Property	Test method	Unit	value
M.F.I	ISO 1133	Dg/min	16
Density	ISO 1183	g/cm <sup>3</sup>	0.9
Flexural Modulus	ISO 178	N/mm <sup>2</sup>	1550
Tensile	ISO R527	N/mm <sup>2</sup>	30
Elongation	ISO R527	%	12
Vicat	ISO 306/A	°C	154
H.D.T	ISO 75/B	°C	95