

KP Plastics

CMP 611

Description:

DANCMP 611 is a compound based on Acrylonitrile-Butadiene-Styrene copolymer with Anti-UV.

Advantages:

High mechanical properties, impact resistance and easy flow, good dimensional stability and chemical resistance.

Characteristics:

Appearance: Granular
Color: Natural
Carrier: Acrylonitrile-Butadiene-Styrene copolymer
Processing Method: Injection molding

Application:

Home appliances, automobile parts, office equipment, sanitary ware, miscellaneous goods, toys, vacuumed cleaner parts, etc.

Properties:

Parameters	Value	Unit	Test Method
Physical			
Melt Flow Index (200°C, 5 kg)	4±1	g/10 min	ASTM D 1238
Density	1.03 ±0.01	gr/cm ³	ASTM D 1505
Mechanical			
Tensile Strength @Peak	37±2	MPa	ASTM D 638
Elongation @Break	28±2	%	ASTM D 638
Notched Izod Impact(23°C)	27±2	KJ/m ²	ISO 180
Elastic Modulus	≥1600	MPa	ASTM D 638
Hardness (15 sec)	72±1	shore D	ASTM D2240

*Test Condition: Samples were prepared by injection molding machine (100 Ton).

Processing Conditions:

It is recommended that ABS should be dried at (80-85 °C) for 3 hours.

Injection Molding:

Rear Temp (°C)	Center Temp (°C)	Center Temp (°C)	Front Temp (°C)	Nozzle Temp (°C)
190-200	200-210	210-220	210-220	215-225
Melt Temp (°C)	Mold Temp (°C)	Filling Speed		
230	60-80	Slow-Mid		

Contact US :

02177784838

+98 09122050173

Info@irplastics.com