

## **CMP 742**

# **Description:**

DANCMP 742 is one of the most widely used industrial thermoplastics. PC-ABS offers the most desirable properties of both materials.

#### Advantages:

High mechanical properties, medium impact and easy flow, good dimensional stability and chemical resistance

## Characteristics:

Appearance: Granular Color: Brown

Carrier Acrylonitrile-Butadiene-Styrene copolymer

Processing Method: Injection molding

#### **Application:**

Home appliances, automobile parts, office equipment, sanitary ware, miscellaneous goods, toys, vacuumed cleaner parts, etc.

## **Properties:**

| Parameters                    | Value      | Unit               | Test Method |  |  |  |
|-------------------------------|------------|--------------------|-------------|--|--|--|
| Physical                      |            |                    |             |  |  |  |
| Melt Flow Index (220°C, 10kg) | 28±2       | g/10 min           | ASTM D 1238 |  |  |  |
| Density                       | 1.03 ±0.02 | gr/cm <sup>3</sup> | ASTM D 1505 |  |  |  |
| <u>Mechanical</u>             |            |                    |             |  |  |  |
| Tensile Strength @Peak        | 37±2       | MPa                | ASTM D 638  |  |  |  |
| Elongation @Break             | 18±3       | %                  | ASTM D 638  |  |  |  |
| Notched Izod Impact(23°C)     | 27±2       | KJ/m <sup>2</sup>  | ISO 180     |  |  |  |
| Elastic Modulus               | ≥1600      | MPa                | ASTM D 638  |  |  |  |
| Colorimetry(De)               | ≤1.5       | -                  | Internal    |  |  |  |

<sup>\*</sup>Test Condition: Samples were prepared by injection molding machine (100 Ton).

# **Processing Conditions:**

It is recommended that ABS should be dried at (80-85 °C) for 3 hours.

# Injection Molding:

| Rear Temp (°C) | Center Temp (°C) | Center Temp (°C) | Front Temp (°C) | Nozzle Temp (°C) |
|----------------|------------------|------------------|-----------------|------------------|
| 190-200        | 200-210          | 210-220          | 210-220         | 215-225          |
| Melt Temp (°C) | Mold Temp (°C)   | Filling Speed    |                 |                  |
| 230            | 60-80            | Slow-Mid         |                 |                  |

**Contact US:** 

02177784838

+98 09122050173

Info@irplastics.com