

Technical Datasheet of Compound CMP 4191

Description:

DANCMP 4191 is polypropylene filled with 20% glass fiber offering better mechanical properties.

Advantages:

High mechanical properties, high impact and easy flow, good dimensional stability and chemical resistance

Characteristics:

Appearance: Granular
Color: Natural
Carrier: PP
Processing Method: Injection molding

Application:

This compound is used in appliance industry, automotive applications, electrical goods, housewares and other utility products.

Properties:

Parameters	Value	Unit	Test Method
Physical			
Melt Flow Index (230°C, 2.16 kg)	5±2	g/10 min	ASTM D 1238
Density	1.05± 0.02	gr/cm ³	ASTM D 1505
Ash Content	20 ± 2	%	ASTM D 5630
Mechanical			
Tensile Strength @Peak	≥65	MPa	ASTM D 638
Elongation @Break	3±2	%	ASTM D 638
Notched Izod Impact(23°C)	12±2	KJ/m ²	ISO 180
Elastic Modulus	≥2300	MPa	ASTM D 638

*Test Condition: Samples were prepared by injection molding machine (100 Ton).


Processing Conditions:


Injection Molding:

Rear Temp (°C)	Center Temp (°C)	Center Temp (°C)	Front Temp (°C)	Nozzle Temp (°C)
200-210	200-210	210-220	220-230	220-230
Melt Temp (°C)	Mold Temp (°C)	Filling Speed		
230	60-80	Slow-Mid		



 Unit 302, Sheydayee BLD, Sazman AB, Tehranpars

 <https://irplastics.com/en>

 +98-21-77784838

